

# Avery® PC MPI 3300 Gloss Series

MPI 3300 / 3301 / 3302 / 3303

Clear Permanent/ Clear Removable / Gray Removable / Gray Permanent Kraft

Revision: New Dated: 6/24/2011

## Uses:

Avery PC MPI 3300 Gloss Series are flexible, calendered vinyl films that deliver vibrant and consistent print images at an exceptional value. Avery PC MPI 3300 and 3303 Gloss feature a clear and gray permanent adhesive designed for short to medium term promotional graphics while the Avery PC MPI 3301 and 3302 offer a clear and gray adhesive for promotional applications requiring removable adhesive performance. These films are well suited for applications such as Point-of-Purchase, Product Identification Labels, as well as Outdoor and General Signage.



**Face:** 3.0 mil (76 microns) Gloss



**Adhesive:** Acrylic  
MPI 3300 - Permanent (clear)  
MPI 3301 - Removable (clear)  
MPI 3302 - Removable (gray)  
MPI 3303 - Permanent (gray)



**Liner:** Clay-Coated Kraft



**Durability:** Up to 4 years (unprinted)

**Application Surfaces:** Flat, simple curves (restricted to non-spill areas)

## Features:

- Consistent Print Performance resulting in vibrant images every time
- Excellent image clarity and color pop
- Easy to handle liner for trouble free converting
- ICC profiles available on Avery website ([www.iccprofiles.averygraphics.com](http://www.iccprofiles.averygraphics.com))

## Conversion:

- |  |  |   |
|--|--|---|
| <input checked="" type="checkbox"/> Thermal Die-Cutting    | <input type="checkbox"/> Thermal Transfer    | <input checked="" type="checkbox"/> Solvent based inkjet    |
| <input checked="" type="checkbox"/> Flat Bed Sign-Cut      | <input type="checkbox"/> Screen Printing     | <input checked="" type="checkbox"/> Mild/Eco Solvent inkjet |
| <input checked="" type="checkbox"/> Drum Roller Sign-Cut   | <input type="checkbox"/> Cold Overlaminating | <input checked="" type="checkbox"/> UV inkjet               |
| <input checked="" type="checkbox"/> Steel Rule Die-Cutting | <input type="checkbox"/> Water based inkjet  | <input checked="" type="checkbox"/> Latex Inkjet            |

Note: Product is not recommended for use on drum digital printers or sheet-fed conversion.

## Common Applications:

- |   |  |   |
|---|--|---|
| <input type="checkbox"/> Fleet              | <input type="checkbox"/> Backlit Signs             | <input type="checkbox"/> Window Graphics            |
| <input type="checkbox"/> Vehicle            | <input checked="" type="checkbox"/> Wall Murals    | <input checked="" type="checkbox"/> Outdoor Signage |
| <input type="checkbox"/> Marine/ Watercraft | <input checked="" type="checkbox"/> POP/ Tradeshow | <input checked="" type="checkbox"/> Floor Graphics  |



SIGN • LIGHTING • GRAPHICS • DISPLAY

*Excellence in Distribution Since 1946*

[www.IECDelivers.com](http://www.IECDelivers.com)

# Avery® PC MPI 3300 Gloss Series

MPI 3300 / 3301 / 3302 / 3303

Clear Perm/ Clear Removable / Gray Removable / Gray Perm Kraft

Revision: 0 Dated: 6/24/2011



## Physical Characteristics:

Property		Value
Caliper, face		3.0 mil (76 µm)
Caliper, adhesive		1.0mil (25 µm)
Dimensional stability		<0.030"(0.762 mm)
		Note: Ink loads in excess of 250% may cause increased shrinkage of the printed film.
Tensile @ 16%		6.0 lb/in (1.1 kg/cm)
Tensile @ Break		12.2 lb/in (2.3 kg/cm)
Elongation		Min 150%
Gloss	Hunter Gloss @ 60	90 ±10
Adhesion: 15 min	Permanent Removable	2.5 lb/in (438 N/m) 1.0-2.0 lb/in (175-350 N/m)
	24 hr Permanent Removable	3.9 lb/in (683 N/m) 1.5-3.0 lb/in (263-525 N/m)
Flammability		Self Extinguishing
Shelf-Life		1 year
Durability	Vertical Exposure	Unprinted – 4 years
Min. Application Temperature		50°F (10°C)
Service Temperature		-40° - 180°F (-40° - 82°C) (Reasonable range of temperatures which would be expected under normal environmental conditions).
Chemical resistance		Resistant to most mild acids, alkalis, and salt solutions.

### Important:

Information on physical and chemical characteristics are based on tests believed to be reliable. The values are intended only as a source of information. This information is given without guaranty and do not constitute a warranty. The purchaser should independently determine, prior to use, the suitability of any material for their specific purpose. (Data represents average values where applicable, and is not intended for specification purposes)

### Warranty:

All statements, technical information and recommendations about Avery Dennison products are based upon tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that Purchaser has independently determined the suitability of such products for its purposes. Avery Dennison products are warranted to be free from defects in material and workmanship for either one year (or the period stated on the specific product information literature in effect at time of delivery, if longer) from date of shipment if said product is properly stored and applied. It is expressly agreed and understood that Avery Dennison's sole obligation and Purchaser's exclusive remedy under this warranty, under any other warranty, express or implied, or otherwise, shall be limited to repair or replacement of defective product without charge at Avery Dennison's plant or at the location of product (at Avery Dennison's election), or in the event replacement or repairs is not commercially practical, to Avery Dennison's issuing Purchaser a credit reasonable in light of the defect in the product.

Avery Dennison's liability for defective products shall not exceed the purchase price paid therefore by Purchaser and in no event shall Avery Dennison be responsible for any incidental or consequential damages whether foreseeable or not, caused by defects in such product, whether such damage occurs or is discovered before or after replacement or credit, and whether or not such damage is caused by Avery Dennison's negligence.

NO EXPRESS WARRANTIES AND NO IMPLIED WARRANTIES, WHETHER OF MERCHANTABILITY OR FITNESS FOR ANY PARTICULAR USE, OR OTHERWISE (EXCEPT AS TO TITLE), OTHER THAN THOSE EXPRESSLY SET FORTH ABOVE WHICH ARE MADE EXPRESSLY IN LIEU OF ALL OTHER WARRANTIES, SHALL APPLY TO PRODUCTS SOLD BY AVERY DENNISON. AVERY DENNISON SPECIFICALLY DISCLAIMS AND EXCLUDES ALL OTHER SUCH WARRANTIES. NO WAIVER, ALTERATION, ADDITION OR MODIFICATION OF THE FOREGOING CONDITIONS SHALL BE VALID UNLESS MADE IN WRITING AND MANUALLY SIGNED BY AN OFFICER OF AVERY DENNISON.



SIGN • LIGHTING • GRAPHICS • DISPLAY

Excellence in Distribution Since 1946

www.IECDelivers.com

# Avery<sup>®</sup> PC MPI 3300 Gloss Series

MPI 3300 / 3301 / 3302 / 3303

Clear Perm/ Clear Removable / Gray Removable / Gray Perm Kraft

Revision: 0      Dated: 6/24/2011



## **Dimensional stability:**

Is measured on a 6" x 6" (150 x 150 mm) aluminum panel to which a specimen has been applied; 72 hours after application the panel is scored in a cross pattern, exposed for 48 hours to 150°F (65°C), after which the shrinkage is measured.

## **Adhesion:**

(FTM-1, FINAT) is measured by peeling a specimen at a 180° angle from a stainless steel panel, 24 hours after the specimen has been applied under standardized conditions. Initial adhesion is measured 15 minutes after application of the specimen.

## **Flammability:**

A specimen applied to aluminum is subjected to the flame of a gas burner for 15 seconds. The film should stop burning within 15 seconds after removal from the flame.

## **Temperature range:**

A specimen applied to stainless steel is exposed at high and low temperatures and brought back to room temperature. 1 hour after exposure the specimen is examined for any deterioration. Note: Prolonged exposure to high and low temperatures in the presence of chemicals such as solvents, acids, dyes, etc. may eventually cause deterioration.

## **Chemical Resistance:**

All chemical tests are conducted with test panels to which a specimen has been applied. 72 hours after application the panels are immersed in the test fluid for the given test period. 1 hour after removing the panel from the fluid, the specimen is examined for any deterioration.

*Revisions are italicized*



SIGN • LIGHTING • GRAPHICS • DISPLAY

*Excellence in Distribution Since 1946*

[www.IECDelivers.com](http://www.IECDelivers.com)